


# Declaration of Conformity in accordance with Regulation (EC) 1935/2004

the manufacturer: Ampri Handelsgesellschaft mbH Benzstr. 16 21423 Winsen (Luhe) Germany

confirms the conformity of article

## 01197 BLUE BASIC-PLUS



disposable nitrile gloves, powderfree

with the rules of the

Regulation (EC) 1935/2004 - article 3, 5, 11, 15 and 17-, german feed and food code – LFGB, Regulation (EC) 10/2011, with regard to the migration behaviour, and the german recommendation XXI of the Federal Institute for Risk Assessment (BfR).

### Specification of the intended use or limitations

The above-mentioned article can be used safely in the preparation and treatment of food. In this process, they may be in direct contact with the following types of food for a short time:

all types		

#### Restriction

The article is not suitable for the following types of food:					
not applicable	not applicable				

The valuation basis for the glove-application is a surface-to-volume ratio of 8,4 dm<sup>2</sup> per 5kg food in accordance with the German BfR.

#### sensory evaluation

simulant solution	conditioning	testing	result
coconut oil	10 minutes 40°C	odour change	no changes
coconut oil	10 minutes 40°C	flavour change	no changes
water	10 minutes 40°C	odour change	no changes
water	10 minutes 40°C	flavour change	no changes



# results of the overall migration

simulant solution	conditioning	overall migration mg/dm <sup>2</sup>	limit mg/dm <sup>2</sup>
acetic acid 3%	10 minutes 40°C	< 2,5 mg/dm <sup>2</sup>	10 mg/dm <sup>2</sup>
ethanol 95%	10 minutes 40°C	7,85 mg/dm <sup>2</sup>	10 mg/dm <sup>2</sup>
Isooctane	5 minutes 20°C	4,85 mg/dm <sup>2</sup>	10 mg/dm <sup>2</sup>
ethanol 10%**	1 hour 40°C	< 1 mg/dm <sup>2</sup>	10 mg/dm <sup>2</sup>

# results of the specific migration

compound	simulant solution	Conditioning or other analytical methods	result	limit
Primary aromatic amines (PAA)	acetic acid 3%	1 hour at room temperature	< 0,02 mg/kg	0,02 mg/l
Polycyclic aromatic hydrocarbons (PAH)	Isooctane	5 minutes 20°C	not detected	10 µg/kg
Phthalates	ethanol 95%	10 minutes 40°C	< 1 mg/kg	9 mg/kg
Formaldehyde	acetic acid 3%	10 minutes 40°C	< 0,02 mg/dm2	3 mg/kg
Acrylonitrile*	acetic acid 3%	10 minutes 40°C	< 0,01 mg/kg	0,01 mg/kg
Acrylonitrile*	olive oil	10 minutes 40°C	< 0,01 mg/kg	0,01 mg/kg
Butadiene*	acetic acid 3%	10 minutes 40°C	< 0,01 mg/kg	0,01 mg/kg
Butadiene*	olive oil	10 minutes 40°C	< 0,01 mg/kg	0,01 mg/kg

## Result total content

compound	simulant solution	Conditioning or other analytical methods	result	limit
Nitrosamines		French Degree 2007-766	not detected	1 µg/dm2
N-nitrosatable Substances		French Degree 2007-766	not detected	1 µg/dm2
Polycyclic aromatic hydrocarbons (PAH)	extraction with toluene	Ultrasonic extraction	< 0,2 mg/kg	
Bisphenol A	extraction with organic solvent	LC-QQQ-Analysis	< 0,1 mg/kg	0,1 mg/kg
Phthalates		extraction with THF/ACN followed by GCMS / LC-MS	passed	
peroxides value		titration with sodiumthiosulphate	not detected	
Volatile organic matters		4 hours 105°C	0,11% w/w	0,5% w/w
Zinc		4 hours 105°C	0,0114	0,03
Cadmium		microwave digestion with sulphuric	< 1 mg/kg	100 mg/kg,
Lead		Acid digestion with ICP detection	0,00000135	0,00003



### Examination of pigments ((for coloured items)

simulant solution	evaluation
acetic acid 3%	passed, no colour transition

## regulation (EU) 2020/1245 heavy metals

simulant solution:	acetic acid 3%
conditioning:	1 hour 40°C

evidence	concentration in mg/kg	limit in mg/kg food or food simulant
Aluminium	< 0,1	1
Antimony	-,	0,04
Arsenic		0,01
Barium	< 0,1	1
Cadmium		0,002
Chromium		ND
Cobalt	< 0,005	0,05
Copper	< 0,5	5
Europium		0,05
Gadolinium		0,05
Iron	< 5	48
Lanthanum		0,05
Lead		0,01
Lithium	< 0,1	0,6
Manganese	< 0,1	0,6
Mercury		0,01
Nickel	< 0,002	0,02
Terbium		0,05
Zinc	< 3	5



Testreport-no. and institute:

(25420)339-474128, Bureau Veritas \*(25422)103-513397, Bureau Veritas \*\*190321-05, AMPri Labor

When used as specified, the overall migration as well as the specific migration do not exceed the legal limits. The examination was conducted in accordance with Regulation (EC) No. 10/2011 (Annex V), including all current amendments and corrections.

The requirements for materials and raw materials of the Plastic Regulation (EC) No. 10/2011 is not applicable for elastomer-protective gloves.



### regulation (EC) 2023/2006

The above article is manufactured in accordance with Good Manufacturing Practices (GMP), i.e. they are produced and controlled with the assurance of compliance with applicable regulations and quality standards.

Ingredients with limited use in food

"dual use substances"

not applicable

Name of the substance	RefNo. (CAS- EINECS-PM and/or E-No)	Limit value [mg/kg]

The traceability according to the regulation (EC) No. 1935/2004 is ensured by the batch number.

Winsen, 18.08.2023

This declaration of conformity has a validity until

18.08.2026